

# ALEXFLOOR SPORTCOAT

## Acrylic Paint for Outdoor Coating

### Description

**ALEXFLOOR Sport coat** is a one component fast drying acrylic-thermoplastic based coating, designed for resist abrasion For asphalt and concrete floor .

### Uses

**ALEXFLOOR SPORTCOAT** is used for outdoor sport surface such as:-

- Play yards.
- Tennis courts.
- Walkways.
- Multi-purpose athletic courts.

### Advantages

- UV- resistance.
- High abrasion and scuffing resistance.
- Water resistant.
- Odourless epoxy.
- Resist atmospheric exposure.
- Easy for use.
- Prevent surface glare to increase visibility.
- Coloured.

### Colors

**ALEXFLOOR SPORTCOAT** is available in a white, green, blue, red and brown colour .

### Packing

**ALEXFLOOR SPORTCOAT** is supplied as a 5.00 kg pail.

### Properties

<b>Density</b>	1.2 to 1.3 gm/cm <sup>3</sup>	
<b>Solid content</b>	55-60 %	
<b>Full cure</b>	3days	25° C
<b>Hand dry</b>	1 days	25° C
<b>Touch to dry</b>	25 min	25° C

### Surface preparation

Remove all loose particle oil, grease, or any defective concrete. The surface is to be laid must be flat and roughened. Surface to receive coating should be dry.

### Guide to application

The material should be mixed in its container by mechanical mixer until a smooth and even consistency is achieved.

### **Application:**

- Porous substrates should be sealed with Primer(ALEXPRIME EP)or (ALEXPRIME AR) prior to application of **ALEXFLOOR SPORTCOAT**.
- It can be applied by brush or roller.

**Coverage:**

0.5 Kg/m<sup>2</sup> 250 microns(D.F.T)

"Two or three Coats is recommended"

**Storage:**

Store out of direct sunlight, clear of the Ground on pallets protected from rainfall  
Avoid excessive compaction and protect from extremes of temperatures

**Shelf life:**

Up to 12 months if stored in unopened containers according to manufacturers instructions

**Safety precautions:**

Avoid contact with eyes, mouth, skin  
persons handling these materials shall Use protective clothing including rubber or plastic gloves.

**Guarantee:**

All precaution is taken in manufacture of each product to comply with the standard of each material.

The data sheet for each product for information only and may be corrected and no liability is accepted for it.

The results may have variation because the method of their use condition under which they are applied cannot be anticipated.

**Technical Service:**

For any technical advice for using the **ALEXCHEM** contact the technical office.

**HEAD OFFICE:**

33 Elamgad St,Miami,Alexandria

[www.alexchem.net](http://www.alexchem.net)

info@alexchem.net

Tel/Fax: +203-5566791

Mob: +20173745566

**FACTORY:**

ELNahda,Karnak-Amraya

Tel: +203-9680828

Fax: +203-9680830