

ALEXPLAST F3



Super Plasticizing High Range Water Reducing Admixture, Early Strength

Description

ALEXPLAST F3 It contains a powerful super plasticizer that allow mixing water to be reduced and concrete strength to be enhanced significantly at early ages.

Uses

- To produce high workability concrete.
- In precast and prestressed concrete where early use of mould are required.
- To reduce permeability.
- Pumped concrete.
- Casting in hot climates.
- When pozzolonic material such as silica fume are used.

Advantages

- Aids pumping by reducing line friction.
- Increase density and reduces porosity resulting in improved water penetration resistance.
- Early strength seven days' results are obtained after three days, twenty eight days results are obtained after seven days.
- Increase cohesion, minimizes segregation and bleeding and gives improved surface finish.

- Enables precast concrete units to be demoulded after 12-16 hrs and earlier for heat/ Steam cured systems.
- No effect for setting time at recommended dose ages.
- Improve physical properties for concrete.
- Increase water proofing properties as it decrease the permeability.

Standards

ALEXPLAST F3 complies with ASTM C494 Types A and F
BS 5075 PART 3

Properties

Colour	Dark Brown liquid	
Specific gravity	1.12	20°C
Chloride content	Nil	
Water Reduction	Reduction up to 20% can be reached depending on materials used and mix design	
Compatibility	Can be used with all types of Portland cements	
Durability	When ALEXPLAST F3 is used for water reduction the increase in density and reduction of permeability improved durability and reduces porosity	

Guide to Application

Mixing:

ALEXPLAST F3 should be added to the mixing water prior to dry mix added.

Coverage:

0.5 to 3.0 lit per 100 kg of used cement
The optimum dosage for **ALEXPLAST F3** should be determined by site trials with the particular concrete mix under prevailing conditions.

Packing:

Is supplied in 20 lit, 210 lit drums, 1000 lit bulk.

Guarantee:

All precaution is taken in manufacture of each product to comply with the standard of each material.

The data sheet for each product for information only and may be corrected and no liability is accepted for it. The results may have variation because the method of their use condition under which they are applied cannot be anticipated.

Technical Service:

For any technical advice for using the **ALEXCHEM** contact the technical office.

Shelf life:

Up to 12 month when stored as recommended

Storage:

Should be stored in shaded areas and is kept within the range 2 °C to 50 °C

Safety precaution

- Avoid contact with eyes, mouth skin, and follow by washing soap and water and any eye contamination should be washed thoroughly with plenty of water and immediate medical treatment sought.

HEAD OFFICE:

12 Ibn saad,45 Miami ,Alexandria
Tel:03-5885431 Fax:03-5885253
mob: 01155444400
Website : www.alexchem.net
Email : info@alexchem.net

FACTORY:

ElNahda- Amrya -Alexandria
Tel/Fax:03-4770313