# **ALEXRUST**



## **Rust Converting Primer**

## **Description**

ALEXRUST is water based rust converter combined with a non pigmented high quality latex metal primer.

It is a unique fluid which chemically Converts rust present on the surface to a black film which resists further corrosion

## <u>Uses</u>

- •Pre-treatment for rusted:
- Structural steel.
- Machinery.
- Gates.
- Railings.
- •Can be used on welds.
- Not recommended for outside hull underwater applications.
- Eliminates need to mechanically blast To white metal in many instances.

# **Advantages**

- Economical.
- •Non-hazardous.
- •Fast effective.
- •Easy to use.
- •Does not require special equipment.
- •Sets a strong bond between paint&metal.
- •Dries quickly.
- •Bonds strongly to metal.

## **Surface preparation**

Surfaces should be brushed clean to remove loose material, dust,dry. Do not apply on surface where the temperatures are below 5°c or above 40°c

#### **Properties**

Volume Solid	40%
Specific Gravity	1.20
Dry to Touch	1 Hour
Vapour Pressure	N/A
Over Coating	4-6 hours

## **Guide to application**

#### Application:

**ALERUST** may be applied by spray,brush or roller.

Two coats are recommended for maximum conversion and protection.

**ALERUST** may be applied to damp surfaces although protection from air is necessary when the film is drying.

#### Coverage:

Yield approximately 15-20m<sup>2</sup> per litre.

## Packing:

Is supplied in 20 litre pails.

#### Storage:

Store out of direct sunlight, clear of the ground on pallets protected from rain fall. protect from extremes of temperatures.

#### Shelf life:

Up to 12 months if stored in unopened Containers.

## Safety precautions:

Avoid contact with eyes, mouth, and skin. Treat splashes to eyes by water. Non toxic.

In the event of prolonged irritation seek medical advice.

#### **Guarantee:**

All precaution is taken in manufacture of each product to comply with the standard of each material.

The data sheet for each product for information only and may be corrected and no liability is accepted for it.

The results may have variation because the method of their use condition under which they are applied cannot be anticipated.

## **Technical Service:**

For any technical advice for using the **ALEXCHEM** contact the technical office.

#### **Technical Service:**

For any technical advice for using the **ALEXCHEM** contact the technical office.

#### **HEAD OFFICE:**

12 Ibn saad,45 Miami ,Alexandria Tel:03-5885431 Fax:03-5885253

mob: 01155444400

Website: www.alexchem.net : info@alexchem.net Email

#### **FACTORY:**

ElNahda- Amrya -Alexandria Tel/Fax:03-4770313