

ALEXTOP 110 S.F

Coloured Cementitious Mortar for Facades

Description

ALEXTOP 110 S.F is a single component for external facades and internal surfaces.
ALEXTOP 110 S.F is easy to apply and use on both dry and wet surfaces.

Uses

- For external facades.
- For internal surfaces.
- For industrial and commercial facilities.

Advantages

- Easy to apply (it requires only mixing with water) and available in different colours.
- Use as a final colour layer on the plaster.
- Select of raw materials is subjected to the highest standard of quality control.
- Non toxic, free from chlorides and nitrates.
- It can be applied by using trowels or spraying machine (Tartasha).

Properties

Colour	Valid in 24 colours and upon request	
Specific Weight	1.7 kg/lit	
Cure Time	25 min	5-35 °C
Thickness	1-2 mm when using trowels	

Guide to application

Surface preparation:

- The surface must be clean, free from dust, oils, grease and loose materials, using spraying water to wet the surface.
- The coloured powder is added gradually to 6-7 lit of water and stir well till reaching the homogenous texture and colour.
- Apply by using trowel or tartasha by using spraying machine.

Coverage:

- From 2 to 2.5 kg/m² in case of using trowel.
- From 4.50 to 5.50 kg/m² in case of using tartasha.

Packing:

It is available in 25 kg

Storage:

Up to 12 months if stored out of direct sun and away from rain, water. Stored in shaded area.

Safety Precaution:

- **ALEXTOP 110 S.F** is non toxic and not harmful while using.
- Remove any contamination from Skin by water and soap

Guarantee:

All precaution is taken in manufacture of each product to comply with the standard of each material.

The data sheet for each product for information only and may be corrected and no liability is accepted for it.

The results may have variation because the method of their use condition under which they are applied cannot be anticipated.

Technical Service:

For any technical advice for using the **ALEXCHEM** contact the technical office.

HEAD OFFICE:

33 Elamgad St, Miami, Alexandria

www.alexchem.net

info@alexchem.net

Tel/Fax: +203-5566791

Mob: +20173745566

FACTORY:

ELNahda, Karnak-Amraya

Tel: +203-9680828

Fax: +203-9680830