

# ALEXTOP G



## Road Marking on Asphalt and Concrete Surfaces

### Description

**ALEXTOP G** is two components, Epoxy coating for long term road marking on asphalt, concrete and brick.

### Uses

- Marking on asphalt, concrete and brick.

### Advantages

- Good abrasive resistance.
- Good adhesion.
- Resistant to water and oil.
- Tough, hard wearing film.
- Fast drying coatings.
- Can be applied to temperature down to -10°C.
- Good chemical resistance.

### Surface preparation

- All surfaces must be sound, clean free from water oil ,grease and other contaminants.

### Properties

Colour	White, yellow and black	
Pot Life	3 hours	20°C
	2 hours	35°C
Density	1.25 g/cm <sup>3</sup>	
Solid volume	70%	
Dry film thickness	50-150µm	
Touch dry	2 hours	
Flash point	27°C	
Full cure	7 days	20°C
	4 days	35°C
Over coating interval	minimum 16 hours	

### Guide to application

#### **Mixing:**

- Mix the two components well until reaching homogenous consistency.

#### **Application:**

- Thinner should only be added after proper mixing of the component.
- Brush, roller or spray can be used for painting.

Volume of thinner		
	Air spray	Brush/Roller
Nozzle size	5 mm	—
Nozzle pressure	15Mpa(2100psi)	—

**Coverage:**

14 m<sup>2</sup>/ lit @ 50 micron D.F.T

**Packing:**

Is supplied in 5 kg, 20 kg

**Shelf life:**

Up to 12 months if stored in unopened Containers according to the manufactured Instructions.

**Guarantee:**

All precaution is taken in manufacture of each product to comply with the standard of each material.

The data sheet for each product for information only and may be corrected and no liability is accepted for it.

The results may have variation because the method of their use condition under which they are applied cannot be anticipated.

**Technical Service:**

For any technical advice for using the **ALEXCHEM** contact the technical office.

**Safety precautions:**

- Avoid contact with eyes, mouth, and skin.
- Treat splashes to skin and eyes immediately,
- If accidentally ingested seek medical attention.
- Product is flammable.

**HEAD OFFICE:**

33 Elamgad St,Miami,Alexandria

[www.alexchem.net](http://www.alexchem.net)

info@alexchem.net

Tel/Fax: +203-5566791

Mob: +20173745566

**FACTORY:**

ELNahda,Karnak-Amraya

Tel: +203-9680828

Fax: +203-9680830